

SPECIFICATIONS

Water Content (%)	38
Dk (35°C, Fatt Units)	9
Refractive Index Dry	1.520
Refractive Index Hydrated (35°C)	1.442
Linear Expansion (mm)	1.205
Radial Expansion (mm)	1.205
Hardness (Shore D)	89
% Transmission (@600 nm)	>95
Standard size	Diameter - 12.70 mm, Thickness - 5.0mm
Standard Colors	Clear, High Blue, Low Blue, Low Green
UV Blocker	Available upon request
Precut	Depth - 1.5mm /2.0mm, Radius - 6.8mm

Note: Optional sizing and colors may be available on request.

MANUFACTURING

Environment Control:

We recommend maintaining a maximum Relative Humidity of 45% at 21±2°C

Diamond Tooling:

Tooling	Radius (mm)
Rough	0.400
Fine	0.300

Machining Recommendations:

Base Curve	Speed (RPM)	Feed (mm/min)	Depth (mm)
Rough	10,000	102	0.50
Fine	9,500	25	0.100
Front Curve	Speed (RPM)	Feed (mm/min)	Depth (mm)
Rough	10,000	76	0.350
Fine	9,500	25	0.100

Benz R&D validates expansion values

Machining parameters and tool specifications are important for optimum surface finish and reaching precise target every time. Benz R&D validates the expansion values, target hitting ability and surface quality of every lot of Benz materials when machined strictly according to recommendations.

HYDRATION/STERILIZATION

Polishing

To polish use XPAL, Alox 721 or comparable material. Polishing should require a maximum of 20 seconds under the above machining conditions.

Hydration

Place lenses into the Borate Buffer pH 7.2 isotonic saline and allow the lens to sit in solution while stirring for a minimum of 12 hours. Hydrate for the minimum time specified at constant temperature ($T = 20 \pm 2^\circ\text{C}$). A minimum of 10 ml per lens should be used for hydration.

After hydration, lenses should be rinsed, autoclaved, and stored in the pH 7.2 buffered saline solution for packaging and sterilization.